BAROQUE FLOORING ®

StoneWalk™ – Rigid Core Solid Resilient Flooring

Technical Specifications
Updated: July 2017

Description:	Solid Resilient Floor with Superior Performance Core
Warranty:	Limited Lifetime
Installation:	Float
Dimensions:	3.5 mm x 6" x 49" nominal planks
Packaging:	24.22 sf/ctn, 52 ctn/plt, 1,259.44 sf/plt, 20 plt/cont, 25,188.8 sf/cont, 1,768 lbs plt wt
Pattern Repeat:	Random repeat, not more than every 6 planks
Construction:	Overall Thickness 3.5 mm Extruded PVC with 12 mil Urethane Wear Layer Stone Plastic Composite Core Grip Backing
Profile:	Valinge CLICK
Edges/Ends:	Micro-Bevel
Wear Finish:	Urethane
Gloss Level:	8%, +/- 2%
Certifications:	Floor Score, Carb II
Country of Origin:	Manufactured in China

TEST DATA – Conducted by SGS Technical Services

ASTM D696-08 Coefficient of Linear Thermal Expansion:	-30℃~30℃：24.67×10-6
ASTM E989-06 Std Classification for Determination of Impact Installation:	IIC 45 db
BS 6853 Toxic Fume/Thermal Resistance:	R value .57 meets requirements
BS EN ISO 26987 Staining and Resistance to Chemicals:	Index 0 - Not Affected
DIN51130 Determination of Anti-Slip Property:	19°<X≤27° Classification R11
EN 1399:1998 Method B Cigarette Resistance:	Rating 5: No visible change
EN 14085 Dimensional Tolerances:	L: 1198mm W: 149.99mm Thickness: 3.89mm
EN 669:1998 Dimensional Variation:	L: .01% W: .02%
EN ISO 23999 Dimensional Stability and Curling after Exposure to Heat:	Curling: 0mm
EN71 Heavy Metal:	Not Detected (<MDL)
EN424 Effect of Simulated Movement of a Furniture Leg:	No Visible Damage
EN425 Effect of a Castor Chair:	No Visible Damage
EN 427 Side Length:	L: 1198.88mm W: 150mm
EN 427 Squareness:	Max Deviation .04mm
EN 427 Straightness:	Max Deviation .08mm
EN428 Overall Thickness:	Avg 3.88mm
EN429 Thickness of Wear:	Avg .38mm
EN433 Residual indentation:	.02 Pass
EN438 Resistance to Impact by Large Diameter Ball (flooring grade laminates):	No visible damage on the surface
EN12667 Thermal Conductivity:	0.101 [W/(mK)]
EN13329 AC level£®AC4£©:	4600 IP Abrasion Class 4
EN ISO 9239-1 Critical flux:	>11
EN ISO 9239-1 Smoke:	103.5
EN14372 Phthalate Test 23P:	Not Detected (<MDL)
ISO 14041 EN12673 Pentachlorophenol (PCP):	Not Detected (<MDL)
VOC-AGBB Test Report-"¢Œƒ:	PASS

Baroque Flooring
16150 Main Circle Drive Suite 130 St. Louis, MO 63017 (636-489-2880)